



**HEAVY-DUTY  
WATERPROOFING  
ROOF MEMBRANE**

**PU-60**



## DESCRIPTION

**FORTRESS Heavy-Duty Waterproofing Roof Membrane** is a one component, highly durable polyurethane modified roof membrane that is ideal for waterproofing roofs like concrete roof, tegula roof and pre-painted roof. With its high UV resistance, flexibility and tough durability, **FORTRESS Heavy-Duty Waterproofing Roof Membrane** can be applied on roof surfaces and left exposed to extreme weather conditions without the need for top coat application.

## COMPOSITION

Polyurethane Modified Emulsion  
Functional Fillers  
Titanium Dioxide

## FEATURES AND BENEFITS

- 100% Waterproof
- High UV Resistance
- Can Withstand Extreme Weather Conditions
- No Topcoat Needed
- Paintable

## APPLICATIONS

- Concrete Roof
- Metal Roof
- Tegula Roof
- Pre-painted Roof

## SURFACE PREPARATION

Surface must be clean, dry, stable and free from dust, dirt, oil, grease and other contaminants that will impede on the adhesion of the coating. All visible cracks should be sealed properly using Greenseal Waterproof Elastomeric Sealant.

**For pre-painted metal roof / Pre-painted tegula roof in good condition:** Surface should be lightly sanded using high grit sandpaper, then clean and dried before applying one (1) coat Prime-R Clear Concrete Primer and Sealer.

**For metal roof without paint:** Apply the recommended metal primer before applying **FORTRESS PU-60** on the surface.

**Unpainted tegula roof:** Surface should be clean and dry before applying **FORTRESS PU-60** on the surface.

**For metal roof with light corrosion:** Treat corrosion with a rust treatment product then apply the recommended metal primer. Apply one (1) coat Prime-R Clear Concrete Primer and Sealer.

A minimum of three (3) coating applications of **FORTRESS PU-60** must be applied on the surface. Stir well before using.



<b>PACKAGING</b>	4 liters, 16 liters
<b>COLOR</b>	Gray
<b>COVERAGE</b>	4 liters - 16.0 sq.m @ 0.25mm. wet film thickness / coat  16 liters - 64.0 sq.m @ 0.25mm. wet film thickness / coat
<b>DRYING TIME</b>	30 mins. @30 C - touch dry 1 hour @30 C - recoat 8 hours. @30 C - dry through



29-D GENERAL TIRONA STREET, CALOOCAN CITY, PHILIPPINES  
PHONE NO. (0917) 891 0539  
[www.campbridge.net](http://www.campbridge.net) • email: [campbridgepaint@gmail.com](mailto:campbridgepaint@gmail.com)